

Appln No. 09/775,315

Amdt date August 23, 2004

Reply to Office action of April 21, 2004

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (Currently Amended) A positive active material for a rechargeable lithium battery comprising ~~[a chemically bonded mixture of]~~:

lithium nickel manganese oxides; and

lithium manganese oxides,

wherein a weight ratio of lithium manganese oxides to the lithium nickel manganese oxides is less than 1:1, providing an excess of lithium nickel manganese oxides.

2. (Currently Amended) The positive active material of claim 1 wherein the lithium nickel manganese oxides is  $\text{Li}_x\text{Ni}_{1-y}\text{Mn}_y\text{O}_{2+z}$  ( $0 < x < 1.3$ , and  $0.1 \leq y \leq 0.5$ ),  $0 \leq z \leq 0.5$ ).

3. (Original) The positive active material of claim 1 wherein the lithium manganese oxides is  $\text{Li}_{1+x}\text{Mn}_{2-x}\text{O}_{4+z}$  ( $0 \leq x \leq 0.3$ , and  $0 \leq z \leq 0.5$ ).

4. (Original) The positive active material of claim 1 wherein the mixing ratio of the lithium nickel manganese oxides and lithium manganese oxides is 90 to 60 : 10 to 40 wt%.

5. - 9. (Canceled).

10. (Currently Amended) A positive active material for a rechargeable lithium battery comprising a chemically bonded mixture of lithium nickel cobalt oxides and lithium manganese oxides produced by mixing lithium nickel cobalt oxides with lithium manganese oxides, the weight ratio of lithium manganese oxides to lithium nickel cobalt oxides being less than 1;

**Appln No. 09/775,315**

**Amdt date August 23, 2004**

**Reply to Office action of April 21, 2004**

adding a binder to the mixture; and

heat-treating the resulting mixture of lithium nickel cobalt oxides and lithium manganese oxides at a [~~low~~] temperature ranging between about 200°C and about 500°C.